## F118 - 11018, Flux Core Arc Welding (FCAW) Welding Process Emission Factors

Γ

CALCULATION METHODS							
Annual Emissions: Ea = Ua x EF (lbs/lb rod) x (1-e) Hourly Emissions: Eh = Uh x EF (lbs/lb rod) x (1-e)							
Hourly Emissions: Eh = Uh x EF (lbs/lb rod) x (1-e) Ea = Annual emissions of each listed toxic air contaminant per welding rod, (lbs/year) Eh = Maximum hourly emissions of each listed toxic air contaminant per welding rod, (lbs/hour) Ua = Annual usage of each welding rod, (lbs/year) Uh = Maximum hourly usage of each welding rod, (lbs/hour) EF = Emission Factor (lbs/lb rod)							
EF = Emission Factor (Ibs/Ib roo	d)						
<ul> <li>Emission Factors:</li> <li>(1) Complete AP-42 information from Final Section 12.19 (1/95): EF = Trace Metal EF (Table 12.19-2)</li> <li>(2) Incomplete AP-42 Final Section 12.19 (1/95): EF = FGR (Table 12.19-1) x FCF x Ci (MSDS)</li> <li>(3) No AP-42 information but known welding process: EF = FGR (District Default) x FCF x Ci (MSDS)</li> <li>(4) District Study or AWMA information: EF = Trace Metal EF</li> <li>(5) Incomplete District Study information: EF = FGR (District Study) x FCF x Ci (MSDS)</li> <li>(*) Incomplete AP-42, District, or AWMA Hexavalent Chromium information: EF = Cr (Total Chromium in Fumes) EF x HCR</li> </ul>							
<ul> <li>NOTES:</li> <li>Emission factors assume "uncontrolled" releases. Emission control methods and efficiencies reported are be applied within the emission calculations.</li> <li>Fume generation rates (FGR) are based on the following: <ul> <li>oEPA AP-42 Final Section 12.19 (1/95) Table 12.19-1 (PM10 EF)</li> <li>oARB, Richard Bode: 0.01 (GMAW, TIG, MIG), 0.02 (SMAW, FCAW), 0.00005 (SAW), 0.05 (unspecified)</li> </ul> </li> <li>Fume Correction Factors (FCF) per District engineering discussions with Industry: <ul> <li>oID.5464 (GMAW, TIG, MIG), 0.2865 (SMAW, FCAW, SAW), 1.0 (unspecified)</li> </ul> </li> <li>Trace metal emission factors are based on the following: <ul> <li>oAWMA Volume 59, 2009, Issue 5 (Pages 619-626) Table 2 and Table 3</li> <li>oEPA AP-42 Final Section 12.19 (1/95) Table 12.19-2</li> <li>oDistrict engineering estimates using rod compositions (Ci) from MSDS</li> </ul> </li> <li>Hexavalent chromium conversion rates (HCR) are per District engineering reviews of studies on welding: <ul> <li>oID.05 (GMAW, TIG, MIG), 0.55 (SMAW), 0.0005 (SAW), 0.10 (FCAW, unspecified)</li> </ul> </li> </ul>							
POLLUTANT	DISTRICT EMISSION FACTORS (lbs/lb rod)	REFERENCE DOCUMENT	FACTOR	(UNITS)	COMMENTS		
NOX							
CO							
SOX							
TOG							
VOC							
	5.70E-02				Assume PM10 = TSP		
voc	5.70E-02 5.70E-02	EPA Table 12.19-1 (1/95) AP-42	57	lb/1000 lbs rod	Assume PM10 = TSP Assume PM10 = Fume Generation Rate (FGR)		
VOC TSP		EPA Table 12.19-1 (1/95) AP-42	57		Assume PM10 = Fume		
VOC TSP PM10		EPA Table 12.19-1 (1/95) AP-42	57		Assume PM10 = Fume		
VOC TSP PM10 Al		EPA Table 12.19-1 (1/95) AP-42	57		Assume PM10 = Fume		

Со					
Cr	9.69E-04	EPA Table 12.19-2 (1/95) AP-42	9.69	0.1 lb/1000 lbs rod	District Procedure (1) EF = Trace Metal EF
Cr(VI)	9.69E-05	AWMA Page 623	10	%	District Procedure (*) EF = Cr EF x HCR
Cu					
Mn	7.04E-04	EPA Table 12.19-2 (1/95) AP-42	7.04	0.1 lb/1000 lbs rod	District Procedure (1) EF = Trace Metal EF
Ni	1.02E-04	EPA Table 12.19-2 (1/95) AP-42	1.02	0.1 lb/1000 lbs rod	District Procedure (1) EF = Trace Metal EF
Р					
Pb					
Crystalline Silica					
v					
Zn					
EFERENCES: PA AP-42 Chapter 12.19: https WMA: https://www.tandfonlir		oduction/files/2020-11/documents/c12 /1047-3289.59.5.619	s19.pdf		

Last Updated on 07/07/2022 by A.Weller