

G122 - NiCu, Gas Metal Arc Welding (GMAW) Welding Process Emission Factors

CALCULATION METHODS

Annual Emissions: $E_a = U_a \times EF \text{ (lbs/lb rod)} \times (1-e)$

Hourly Emissions: $E_h = U_h \times EF \text{ (lbs/lb rod)} \times (1-e)$

E_a = Annual emissions of each listed toxic air contaminant per welding rod, (lbs/year)

E_h = Maximum hourly emissions of each listed toxic air contaminant per welding rod, (lbs/hour)

U_a = Annual usage of each welding rod, (lbs/year)

U_h = Maximum hourly usage of each welding rod, (lbs/hour)

EF = Emission Factor (lbs/lb rod)

Emission Factors:

(1) Complete AP-42 information from Final Section 12.19 (1/95): EF = Trace Metal EF (Table 12.19-2)

(2) Incomplete AP-42 Final Section 12.19 (1/95): EF = FGR (Table 12.19-1) x FCF x C_i (MSDS)

(3) No AP-42 information but known welding process: EF = FGR (District Default) x FCF x C_i (MSDS)

(4) District Study or AWMA information: EF = Trace Metal EF

(5) Incomplete District Study information: EF = FGR (District Study) x FCF x C_i (MSDS)

(*) Incomplete AP-42, District, or AWMA Hexavalent Chromium information: EF = Cr (Total Chromium in Fumes) EF x HCR

NOTES:

- Emission factors assume "uncontrolled" releases. Emission control methods and efficiencies reported are to be applied within the emission calculations.
- Fume generation rates (FGR) are based on the following:
 - EPA AP-42 Final Section 12.19 (1/95) Table 12.19-1 (PM10 EF)
 - ARB, Richard Bode: 0.01 (GMAW, TIG, MIG), 0.02 (SMAW, FCAW), 0.00005 (SAW), 0.05 (unspecified)
- Fume Correction Factors (FCF) per District engineering discussions with Industry:
 - 0.5464 (GMAW, TIG, MIG), 0.2865 (SMAW, FCAW, SAW), 1.0 (unspecified)
- Trace metal emission factors are based on the following:
 - AWMA Volume 59, 2009, Issue 5 (Pages 619-626) Table 2 and Table 3
 - EPA AP-42 Final Section 12.19 (1/95) Table 12.19-2
 - District engineering estimates using rod compositions (C_i) from MSDS
- Hexavalent chromium conversion rates (HCR) are per District engineering reviews of studies on welding:
 - 0.05 (GMAW, TIG, MIG), 0.55 (SMAW), 0.0005 (SAW), 0.10 (FCAW, unspecified)

POLLUTANT	DISTRICT EMISSION FACTORS (lbs/lb rod)	REFERENCE DOCUMENT	FACTOR	(UNITS)	COMMENTS
NOX					
CO					
SOX					
TOG					
VOC					
TSP	2.00E-03				Assume PM10 = TSP
PM10	2.00E-03	EPA Table 12.19-1 (1/95) AP-42	2	lb/1000 lbs rod	Assume PM10 = Fume Generation Rate (FGR)
Al	1.14E-06	Historical Welding Study SDS - Pinnacle ERNiCu-7 (60)	0.104	wt%	District Procedure (2) EF = FGR x FCF x C_i
Al2O3					
Be					
Cd					

Co					
Cr	1.00E-06	EPA Table 12.19-2 (1/95) AP-42	0.01	0.1 lb/1000 lbs rod	District Procedure (1) EF = Trace Metal EF
Cr(VI)	5.00E-08	AWMA Page 623	5	%	District Procedure (*) EF = Cr EF x HCR
Cu	3.29E-04	Historical Welding Study SDS - Pinnacle ERNiCu-7 (60)	30.07	wt%	District Procedure (2) EF = FGR x FCF x Ci
Mn	2.20E-05	EPA Table 12.19-2 (1/95) AP-42	0.22	0.1 lb/1000 lbs rod	District Procedure (1) EF = Trace Metal EF
Ni	4.51E-04	EPA Table 12.19-2 (1/95) AP-42	4.51	0.1 lb/1000 lbs rod	District Procedure (1) EF = Trace Metal EF
P	2.19E-08	Historical Welding Study SDS - Pinnacle ERNiCu-7 (60)	0.002	wt%	District Procedure (2) EF = FGR x FCF x Ci
Pb					
Crystalline Silica					
V					
Zn					

REFERENCES:

EPA AP-42 Chapter 12.19: <https://www.epa.gov/sites/production/files/2020-11/documents/c12s19.pdf>
 AWMA: <https://www.tandfonline.com/doi/abs/10.3155/1047-3289.59.5.619>