

S125 - 9018, Shielded Metal Arc Welding (SMAW) Welding Process Emission Factors

CALCULATION METHODS

Annual Emissions: $E_a = U_a \times EF \text{ (lbs/lb rod)} \times (1-e)$
 Hourly Emissions: $E_h = U_h \times EF \text{ (lbs/lb rod)} \times (1-e)$

E_a = Annual emissions of each listed toxic air contaminant per welding rod, (lbs/year)
 E_h = Maximum hourly emissions of each listed toxic air contaminant per welding rod, (lbs/hour)
 U_a = Annual usage of each welding rod, (lbs/year)
 U_h = Maximum hourly usage of each welding rod, (lbs/hour)
 EF = Emission Factor (lbs/lb rod)

Emission Factors:

- (1) Complete AP-42 information from Final Section 12.19 (1/95): EF = Trace Metal EF (Table 12.19-2)
- (2) Incomplete AP-42 Final Section 12.19 (1/95): EF = FGR (Table 12.19-1) x FCF x Ci (MSDS)
- (3) No AP-42 information but known welding process: EF = FGR (District Default) x FCF x Ci (MSDS)
- (4) District Study or AWMA information: EF = Trace Metal EF
- (5) Incomplete District Study information: EF = FGR (District Study) x FCF x Ci (MSDS)
- (*) Incomplete AP-42, District, or AWMA Hexavalent Chromium information: EF = Cr (Total Chromium in Fumes) EF x HCR

NOTES:

- Emission factors assume "uncontrolled" releases. Emission control methods and efficiencies reported are to be applied within the emission calculations.
- Fume generation rates (FGR) are based on the following:
 - EPA AP-42 Final Section 12.19 (1/95) Table 12.19-1 (PM10 EF)
 - ARB, Richard Bode: 0.01 (GMAW, TIG, MIG), 0.02 (SMAW, FCAW), 0.00005 (SAW), 0.05 (unspecified)
- Fume Correction Factors (FCF) per District engineering discussions with Industry:
 - 0.5464 (GMAW, TIG, MIG), 0.2865 (SMAW, FCAW, SAW), 1.0 (unspecified)
- Trace metal emission factors are based on the following:
 - AWMA Volume 59, 2009, Issue 5 (Pages 619-626) Table 2 and Table 3
 - EPA AP-42 Final Section 12.19 (1/95) Table 12.19-2
 - District engineering estimates using rod compositions (Ci) from MSDS
- Hexavalent chromium conversion rates (HCR) are per District engineering reviews of studies on welding:
 - 0.05 (GMAW, TIG, MIG), 0.55 (SMAW), 0.0005 (SAW), 0.10 (FCAW, unspecified)

| POLLUTANT | DISTRICT EMISSION FACTORS (lbs/lb rod) | REFERENCE DOCUMENT | FACTOR | (UNITS) | COMMENTS |
|-----------|--|--------------------------------|--------|-----------------|--|
| NOX | | | | | |
| CO | | | | | |
| SOX | | | | | |
| TOG | | | | | |
| VOC | | | | | |
| TSP | 1.69E-02 | | | | Assume PM10 = TSP |
| PM10 | 1.69E-02 | EPA Table 12.19-1 (1/95) AP-42 | 16.9 | lb/1000 lbs rod | Assume PM10 = Fume Generation Rate (FGR) |
| Al | | | | | |
| Al2O3 | | | | | |
| Be | | | | | |
| Cd | | | | | |

| | | | | | |
|---------------------------|----------|--------------------------------|------|------------------------|---|
| Co | | | | | |
| Cr | 2.12E-04 | EPA Table 12.19-2 (1/95) AP-42 | 2.12 | 0.1 lb/1000 lbs rod | District Procedure (1) EF = Trace Metal EF |
| Cr(VI) | 1.17E-04 | AWMA Page 623 | 55 | % | District Procedure (*) EF = Cr EF x HCR |
| Cu | | | | | |
| Mn | 7.83E-04 | EPA Table 12.19-2 (1/95) AP-42 | 7.83 | 0.1 lb/1000 lbs rod | District Procedure (1) EF = Trace Metal EF |
| Ni | 1.30E-05 | EPA Table 12.19-2 (1/95) AP-42 | 0.13 | 0.1 lb/1000 lbs rod | District Procedure (1) EF = Trace Metal EF |
| P | | | | | |
| Pb | | | | | |
| Crystalline Silica | | | | | |
| V | | | | | |
| Zn | | | | | |

REFERENCES:

EPA AP-42 Chapter 12.19: <https://www.epa.gov/sites/production/files/2020-11/documents/c12s19.pdf>
 AWMA: <https://www.tandfonline.com/doi/abs/10.3155/1047-3289.59.5.619>

Last Updated on 07/07/2022 by A.Weller